



HAL
open science

Crystal structure of alluaudite-type $\text{NaMg}_3(\text{HPO}_4)_2(\text{PO}_4)$

Ahmed Ould Saleck, Abderrazzak Assani, Mohamed Saadi, Cyrille Albert-Mercier, Claudine Follet-Houttemane, Lahcen El Ammari

► **To cite this version:**

Ahmed Ould Saleck, Abderrazzak Assani, Mohamed Saadi, Cyrille Albert-Mercier, Claudine Follet-Houttemane, et al.. Crystal structure of alluaudite-type $\text{NaMg}_3(\text{HPO}_4)_2(\text{PO}_4)$. Acta crystallographica Section E: Crystallographic communications [2015-..], 2015, 71 (7), pp.813-815. 10.1107/S205698901501155X . hal-03116322

HAL Id: hal-03116322

<https://uphf.hal.science/hal-03116322v1>

Submitted on 6 Jul 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution 4.0 International License

Keywords: crystal structure; transition metal phosphates; alluaudite structure type; hydrothermal synthesis; hydrogen bonding

CCDC reference: 1406819

Supporting information: this article has supporting information at journals.iucr.org/e

Crystal structure of alluaudite-type $\text{NaMg}_3(\text{HPO}_4)_2(\text{PO}_4)$

Ahmed Ould Saleck,^{a,b*} Abderrazzak Assani,^a Mohamed Saadi,^a Cyrille Mercier,^b Claudine Follet^b and Lahcen El Ammari^a


^aLaboratoire de Chimie du Solide Appliquée, Faculté des Sciences, Université Mohammed V, Avenue Ibn Battouta, BP 1014, Rabat, Morocco, and ^bLaboratoire des Matériaux Céramiques et Procédés Associés, EA2443, Université de Valenciennes et du Hainaut-Cambrésis, Boulevard Charles de Gaulle, BP 59600, Maubeuge, France. *Correspondence e-mail: a_ouldsaleck@yahoo.fr

The title compound, sodium trimagnesium bis(hydrogen phosphate) phosphate, was obtained under hydrothermal conditions. In the crystal, two types of $[\text{MgO}_6]$ octahedra, one with point group symmetry 2, share edges to build chains extending parallel to $[10\bar{1}]$. These chains are linked together by two kinds of phosphate tetrahedra, HPO_4 and PO_4 , the latter with point group symmetry 2. The three-dimensional framework delimits two different types of channels extending along $[001]$. One channel hosts the Na^+ cations (site symmetry 2) surrounded by eight O atoms, with Na–O bond lengths varying between 2.2974 (13) and 2.922 (2) Å. The OH group of the HPO_4 tetrahedron points into the other type of channel and exhibits a strong hydrogen bond to an O atom of the PO_4 tetrahedron on the opposite side.

1. Chemical context

By means of hydrothermal processes (Demazeau, 2008; Yoshimura & Byrappa, 2008), we have previously succeeded in the isolation of the mixed-valence manganese phosphates $M\text{Mn}^{\text{II}}\text{Mn}^{\text{III}}(\text{PO}_4)_3$ ($M = \text{Ba}, \text{Pb}, \text{Sr}$) adopting the $\alpha\text{-CrPO}_4$ structure type (Assani *et al.*, 2013; Alhakmi *et al.*, 2013*a,b*). In addition, within the pseudo-ternary systems $\text{Ag}_2\text{O}-\text{MO}-\text{P}_2\text{O}_5$, hydrothermal syntheses have allowed us to obtain other $\alpha\text{-CrPO}_4$ isotype phosphates, *viz.* $\text{Ag}_2\text{M}_3(\text{HPO}_4)(\text{PO}_4)_2$ ($M = \text{Co}, \text{Ni}$) while $\text{AgMg}_3(\text{HPO}_4)_2(\text{PO}_4)$ is found to adopt the alluaudite structure type (Assani *et al.*, 2011*a,b,c*). Other hydrothermally grown phosphates with the alluaudite structure include $\text{AgCo}_3(\text{HPO}_4)_2(\text{PO}_4)$ (Guesmi & Driss, 2002), $\text{AgNi}_3(\text{HPO}_4)_2(\text{PO}_4)$ (Ben Smail & Jouini, 2002), $A\text{Mn}_3(\text{HPO}_4)_2(\text{PO}_4)$ ($A = \text{Na}, \text{Ag}$) (Leroux *et al.*, 1995*a,b*) and $\text{NaCo}_3(\text{HPO}_4)_2(\text{PO}_4)$ (Lii & Shih, 1994). Phosphates belonging to either the $\alpha\text{-CrPO}_4$ or alluaudite structure type or derivatives thereof are still in the focus of research owing to their promising applications as battery materials (Trad *et al.*, 2010; Essehli *et al.*, 2015*a,b*; Huang *et al.*, 2015).

The crystal structures of alluaudite-type phosphates exhibit channels in which the monovalent cations are localized. Indeed, this is strongly required for conductivity properties. The crystal structure of alluaudite can be formulated by the general formula $(A1)(A2)(M1)(M2)_2(\text{PO}_4)_3$, (Moore & Ito, 1979). The two A sites can be occupied by either mono- or divalent medium-sized cations while the two M cationic sites correspond to an octahedral environment generally occupied by transition metal cations. On the basis of literature research, it has been shown that the hydrothermal process allows, in general, stoichiometric phases to be obtained while solid-state






Figure 1
The principal building units in the structure of the title compound. Displacement ellipsoids are drawn at the 50% probability level. Hydrogen bonds are indicated by dashed lines [Symmetry codes: (i) $x + \frac{1}{2}, y + \frac{1}{2}, z$; (ii) $-x + \frac{3}{2}, y + \frac{1}{2}, -z + \frac{1}{2}$; (iii) $-x + \frac{3}{2}, -y + \frac{3}{2}, -z + 1$; (iv) $-x + \frac{3}{2}, -y + \frac{3}{2}, -z$; (v) $-x + 1, -y + 1, -z$; (vi) $-x + 1, y, -z + \frac{1}{2}$; (vii) $x, -y + 1, z + \frac{1}{2}$; (viii) $x - \frac{1}{2}, -y + \frac{3}{2}, z - \frac{1}{2}$; (ix) $-x + 2, y, -z + \frac{3}{2}$; (x) $-x + 2, -y + 1, -z + 1$; (xi) $x + \frac{1}{2}, -y + \frac{1}{2}, z + \frac{1}{2}$; (xii) $-x + \frac{3}{2}, -y + \frac{1}{2}, -z + 1$; (xiii) $x, -y + 1, z - \frac{1}{2}$]

reactions give rather a statistical distribution of cations on either the *A* or *M* sites, leading to non-stoichiometric compounds (Bouraima *et al.*, 2015; Khmiyas *et al.*, 2015).

In line with our focus of interest, we hydrothermally synthesized the compound $\text{NaMg}_3(\text{PO}_4)_2(\text{HPO}_4)_2$ and report here its crystal structure.

2. Structural commentary

The principal building units of the allaudite structure of the title compound are represented in Fig. 1. The three atoms




Figure 2
A sheet resulting from the linkage of kinked chains *via* vertices of PO_4 tetrahedra.

Table 1
Selected bond lengths (\AA).

| | | | |
|-----------------------|-------------|-----------------------|-------------|
| Mg1—O3 ⁱ | 2.1224 (13) | Na1—O3 | 2.8840 (19) |
| Mg1—O1 ⁱⁱ | 2.1312 (12) | Na1—O1 ^{vii} | 2.922 (2) |
| Mg1—O4 | 2.1669 (14) | P1—O1 ^{viii} | 1.5372 (12) |
| Mg2—O6 | 2.0234 (13) | P1—O1 | 1.5372 (12) |
| Mg2—O3 ⁱⁱ | 2.0686 (13) | P1—O2 ^{viii} | 1.5476 (13) |
| Mg2—O2 | 2.0696 (14) | P1—O2 | 1.5476 (13) |
| Mg2—O5 ⁱⁱⁱ | 2.0729 (13) | P2—O5 | 1.5234 (12) |
| Mg2—O5 ^{iv} | 2.0955 (13) | P2—O6 | 1.5263 (12) |
| Mg2—O1 ^v | 2.1153 (14) | P2—O3 | 1.5349 (13) |
| Na1—O6 | 2.2974 (13) | P2—O4 | 1.5806 (13) |
| Na1—O6 ^{vi} | 2.4386 (13) | | |

Symmetry codes: (i) $x - \frac{1}{2}, -y + \frac{1}{2}, z - \frac{1}{2}$; (ii) $x, -y + 1, z - \frac{1}{2}$; (iii) $-x + \frac{1}{2}, y + \frac{1}{2}, -z + \frac{1}{2}$; (iv) $x, -y + 1, z + \frac{1}{2}$; (v) $-x + \frac{1}{2}, -y + \frac{3}{2}, -z + 1$; (vi) $-x + 1, -y + 1, -z + 1$; (vii) $x + \frac{1}{2}, -y + \frac{3}{2}, z + \frac{1}{2}$; (viii) $-x, y, -z + \frac{1}{2}$.

Table 2
Hydrogen-bond geometry ($\text{\AA}, ^\circ$).

| <i>D</i> —H··· <i>A</i> | <i>D</i> —H | H··· <i>A</i> | <i>D</i> ··· <i>A</i> | <i>D</i> —H··· <i>A</i> |
|-------------------------|-------------|---------------|-----------------------|-------------------------|
| O4—H4···O2 | 0.93 | 1.57 | 2.4932 (17) | 174 |

Mg1, Na1 and P1 are located on a twofold rotation axis (Wyckoff position 4*e*). Selected interatomic distances are compiled in Table 1. The three-dimensional framework of this structure consists of kinked chains of edge-sharing MgO_6 octahedra running parallel to $[10\bar{1}]$. The chains are held together by regular P1O_4 phosphate groups, forming sheets perpendicular to $[010]$, as shown in Fig. 2. The stacked sheets delimit two types of channels along $[001]$. One of the channels is occupied by Na^+ cations surrounded by eight oxygen atoms (Table 1), whereas the second channel contains the hydrogen atoms of the HP2O_4 tetrahedra, as shown in Fig. 3. They form strong hydrogen bonds (Table 2, Figs. 1 and 3) with one of the oxygen atoms of PO_4 tetrahedra on opposite sides.




Figure 3
Polyhedral representation of the $\text{NaMg}_3(\text{HPO}_4)_2(\text{PO}_4)$ structure showing channels along $[001]$. The O—H···O hydrogen bonds are indicated by dashed lines.

Table 3

Experimental details.

| | |
|---|---|
| Crystal data | |
| Chemical formula | NaMg ₃ (HPO ₄) ₂ (PO ₄) |
| <i>M_r</i> | 382.85 |
| Crystal system, space group | Monoclinic, <i>C2/c</i> |
| Temperature (K) | 296 |
| <i>a</i> , <i>b</i> , <i>c</i> (Å) | 11.8064 (6), 12.0625 (7), 6.4969 (4) |
| β (°) | 113.805 (2) |
| <i>V</i> (Å ³) | 846.54 (8) |
| <i>Z</i> | 4 |
| Radiation type | Mo <i>K</i> α |
| μ (mm ⁻¹) | 1.06 |
| Crystal size (mm) | 0.36 × 0.24 × 0.18 |
| Data collection | |
| Diffractometer | Bruker X8 APEX |
| Absorption correction | Multi-scan (<i>SADABS</i> ; Bruker, 2009) |
| <i>T_{min}</i> , <i>T_{max}</i> | 0.504, 0.748 |
| No. of measured, independent and observed [<i>I</i> > 2 σ (<i>I</i>)] reflections | 9797, 1291, 1138 |
| <i>R_{int}</i> | 0.038 |
| (<i>sin</i> θ / λ) _{max} (Å ⁻¹) | 0.714 |
| Refinement | |
| <i>R</i> [<i>F</i> ² > 2 σ (<i>F</i> ²)], <i>wR</i> (<i>F</i> ²), <i>S</i> | 0.025, 0.072, 1.09 |
| No. of reflections | 1291 |
| No. of parameters | 88 |
| H-atom treatment | H-atom parameters constrained |
| $\Delta\rho_{\max}$, $\Delta\rho_{\min}$ (e Å ⁻³) | 0.57, -0.54 |

Computer programs: *APEX2* and *SAINT* (Bruker, 2009), *SHELXS* (Sheldrick, 2008), *SHELXL2013* (Sheldrick, 2015), *ORTEP-3 for Windows* (Farrugia, 2012), *DIAMOND* (Brandenburg, 2006) and *pubCIF* (Westrip, 2010).

3. Synthesis and crystallization

Colourless parallelepiped-shaped crystals of the title compound were grown under hydrothermal conditions, starting from a mixture of Na₄P₂O₇·10H₂O, MgO and H₃PO₄ (85 wt%) in the molar ratio Na₄P₂O₇·10H₂O:MgO:H₃PO₄ = 1:3:3. The hydrothermal reaction was conducted in a 23 ml Teflon-lined autoclave, filled to 50% with distilled water and under autogenous pressure at 483 K for four days.

4. Refinement

Crystal data, data collection and structure refinement details are summarized in Table 3. The minimum and maximum electron densities are located 0.71 and 0.17 Å⁻³ from O5 and H4, respectively. The O-bound H atom was initially located in a difference map and refined with an O–H distance restraint of 0.93 Å, and with *U*_{iso}(H) = 1.5*U*_{eq}(O).

Acknowledgements

The authors thank the Unit of Support for Technical and Scientific Research (UATRS, CNRST) for the X-ray measurements and Mohammed V University, Rabat, Morocco, for financial support.

References

- Alhakmi, G., Assani, A., Saadi, M. & El Ammari, L. (2013*a*). *Acta Cryst.* **E69**, i40.
- Alhakmi, G., Assani, A., Saadi, M., Follet, C. & El Ammari, L. (2013*b*). *Acta Cryst.* **E69**, i56.
- Assani, A., El Ammari, L., Zriouil, M. & Saadi, M. (2011*a*). *Acta Cryst.* **E67**, i41.
- Assani, A., El Ammari, L., Zriouil, M. & Saadi, M. (2011*b*). *Acta Cryst.* **E67**, i40.
- Assani, A., Saadi, M., Alhakmi, G., Houmadi, E. & El Ammari, L. (2013). *Acta Cryst.* **E69**, i60.
- Assani, A., Saadi, M., Zriouil, M. & El Ammari, L. (2011*c*). *Acta Cryst.* **E67**, i5.
- Ben Smail, R. & Jouini, T. (2002). *Acta Cryst.* **C58**, i61–i62.
- Bouraima, A., Assani, A., Saadi, M., Makani, T. & El Ammari, L. (2015). *Acta Cryst.* **E71**, 558–560.
- Brandenburg, K. (2006). *DIAMOND*. Crystal Impact GbR, Bonn, Germany.
- Bruker (2009). *APEX2*, *SAINT* and *SADABS*. Bruker AXS Inc., Madison, Wisconsin, USA.
- Demazeau, G. (2008). *J. Mater. Sci.* **43**, 2104–2114.
- Essehli, R., Belharouak, I., Ben Yahia, H., Chamoun, R., Orayech, B., El Bali, B., Bouziane, K., Zhoue, X. L. & Zhoue, Z. (2015*b*). *Dalton Trans.* **44**, 4526–4532.
- Essehli, R., Belharouak, I., Ben Yahia, H., Maher, K., Abouimrane, A., Orayech, B., Calder, S., Zhou, X. L., Zhou, Z. & Sun, Y.-K. (2015*a*). *Dalton Trans.* **44**, 7881–7886.
- Farrugia, L. J. (2012). *J. Appl. Cryst.* **45**, 849–854.
- Guesmi, A. & Driss, A. (2002). *Acta Cryst.* **C58**, i16–i17.
- Huang, W., Li, B., Saleem, M. F., Wu, X., Li, J., Lin, J., Xia, D., Chu, W. & Wu, Z. (2015). *Chem. Eur. J.* **21**, 851–860.
- Khmiyas, J., Assani, A., Saadi, M. & El Ammari, L. (2015). *Acta Cryst.* **E71**, 690–692.
- Leroux, F., Mar, A., Guyomard, D. & Piffard, Y. (1995*a*). *J. Solid State Chem.* **117**, 206–212.
- Leroux, F., Mar, A., Payen, C., Guyomard, D., Verbaere, A. & Piffard, Y. (1995*b*). *J. Solid State Chem.* **115**, 240–246.
- Lii, K.-H. & Shih, P.-F. (1994). *Inorg. Chem.* **33**, 3028–3031.
- Moore, P. B. & Ito, J. (1979). *Mineral. Mag.* **43**, 227–35.
- Sheldrick, G. M. (2008). *Acta Cryst.* **A64**, 112–122.
- Sheldrick, G. M. (2015). *Acta Cryst.* **C71**, 3–8.
- Trad, K., Carlier, D., Croguennec, L., Wattiaux, A., Ben Amara, M. & Delmas, C. (2010). *Chem. Mater.* **22**, 5554–5562.
- Westrip, S. P. (2010). *J. Appl. Cryst.* **43**, 920–925.
- Yoshimura, M. & Byrappa, K. (2008). *J. Mater. Sci.* **43**, 2085–2103.

supporting information

Acta Cryst. (2015). E71, 813-815 [doi:10.1107/S205698901501155X]

Crystal structure of alluaudite-type $\text{NaMg}_3(\text{HPO}_4)_2(\text{PO}_4)$

Ahmed Ould Saleck, Abderrazzak Assani, Mohamed Saadi, Cyrille Mercier, Claudine Follet and Lahcen El Ammari

Computing details

Data collection: *APEX2* (Bruker, 2009); cell refinement: *SAINTE* (Bruker, 2009); data reduction: *SAINTE* (Bruker, 2009); program(s) used to solve structure: *SHELXS* (Sheldrick, 2008); program(s) used to refine structure: *SHELXL2013* (Sheldrick, 2015); molecular graphics: *ORTEP-3 for Windows* (Farrugia, 2012) and *DIAMOND* (Brandenburg, 2006); software used to prepare material for publication: *publCIF* (Westrip, 2010).

Sodium trimagnesium bis(hydrogen phosphate) phosphate

Crystal data

$\text{NaMg}_3(\text{HPO}_4)_2(\text{PO}_4)$
 $M_r = 382.85$
 Monoclinic, $C2/c$
 $a = 11.8064$ (6) Å
 $b = 12.0625$ (7) Å
 $c = 6.4969$ (4) Å
 $\beta = 113.805$ (2)°
 $V = 846.54$ (8) Å³
 $Z = 4$

$F(000) = 760$
 $D_x = 3.004$ Mg m⁻³
 Mo $K\alpha$ radiation, $\lambda = 0.71073$ Å
 Cell parameters from 1291 reflections
 $\theta = 2.5\text{--}30.5^\circ$
 $\mu = 1.06$ mm⁻¹
 $T = 296$ K
 Block, colourless
 $0.36 \times 0.24 \times 0.18$ mm

Data collection

Bruker X8 APEX
 diffractometer
 Radiation source: fine-focus sealed tube
 Graphite monochromator
 φ and ω scans
 Absorption correction: multi-scan
 (*SADABS*; Bruker, 2009)
 $T_{\min} = 0.504$, $T_{\max} = 0.748$

9797 measured reflections
 1291 independent reflections
 1138 reflections with $I > 2\sigma(I)$
 $R_{\text{int}} = 0.038$
 $\theta_{\max} = 30.5^\circ$, $\theta_{\min} = 2.5^\circ$
 $h = -16 \rightarrow 16$
 $k = -17 \rightarrow 17$
 $l = -9 \rightarrow 8$

Refinement

Refinement on F^2
 Least-squares matrix: full
 $R[F^2 > 2\sigma(F^2)] = 0.025$
 $wR(F^2) = 0.072$
 $S = 1.09$
 1291 reflections
 88 parameters
 0 restraints

Hydrogen site location: difference Fourier map
 H-atom parameters constrained
 $w = 1/[\sigma^2(F_o^2) + (0.0362P)^2 + 1.4203P]$
 where $P = (F_o^2 + 2F_c^2)/3$
 $(\Delta/\sigma)_{\max} < 0.001$
 $\Delta\rho_{\max} = 0.57$ e Å⁻³
 $\Delta\rho_{\min} = -0.54$ e Å⁻³

Special details

Geometry. All e.s.d.'s (except the e.s.d. in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell e.s.d.'s are taken into account individually in the estimation of e.s.d.'s in distances, angles and torsion angles; correlations between e.s.d.'s in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell e.s.d.'s is used for estimating e.s.d.'s involving l.s. planes.

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (\AA^2)

| | <i>x</i> | <i>y</i> | <i>z</i> | $U_{\text{iso}}^*/U_{\text{eq}}$ |
|-----|--------------|--------------|--------------|----------------------------------|
| Mg1 | 0.0000 | 0.27947 (7) | 0.2500 | 0.00857 (18) |
| Mg2 | 0.29000 (6) | 0.66219 (5) | 0.37489 (10) | 0.00643 (14) |
| Na1 | 0.5000 | 0.52321 (14) | 0.7500 | 0.0308 (4) |
| P1 | 0.0000 | 0.68659 (5) | 0.2500 | 0.00564 (14) |
| P2 | 0.28093 (4) | 0.38887 (3) | 0.38603 (7) | 0.00494 (11) |
| O1 | 0.03662 (11) | 0.75858 (10) | 0.4624 (2) | 0.0078 (2) |
| O2 | 0.10795 (12) | 0.61003 (10) | 0.2634 (2) | 0.0084 (2) |
| O3 | 0.34567 (12) | 0.32859 (10) | 0.6116 (2) | 0.0073 (2) |
| O4 | 0.14051 (11) | 0.40754 (10) | 0.3420 (2) | 0.0085 (2) |
| H4 | 0.1241 | 0.4816 | 0.3033 | 0.013* |
| O5 | 0.28443 (11) | 0.32046 (10) | 0.1916 (2) | 0.0068 (2) |
| O6 | 0.34273 (12) | 0.50140 (10) | 0.4000 (2) | 0.0076 (2) |

Atomic displacement parameters (\AA^2)

| | U^{11} | U^{22} | U^{33} | U^{12} | U^{13} | U^{23} |
|-----|------------|--------------|------------|---------------|--------------|---------------|
| Mg1 | 0.0081 (4) | 0.0088 (4) | 0.0094 (4) | 0.000 | 0.0041 (3) | 0.000 |
| Mg2 | 0.0073 (3) | 0.0057 (3) | 0.0067 (3) | 0.0004 (2) | 0.0031 (2) | 0.0001 (2) |
| Na1 | 0.0118 (6) | 0.0691 (11) | 0.0091 (6) | 0.000 | 0.0016 (5) | 0.000 |
| P1 | 0.0051 (3) | 0.0063 (3) | 0.0044 (3) | 0.000 | 0.0007 (2) | 0.000 |
| P2 | 0.0060 (2) | 0.00431 (19) | 0.0043 (2) | -0.00006 (14) | 0.00177 (16) | -0.00011 (14) |
| O1 | 0.0063 (6) | 0.0110 (5) | 0.0054 (5) | -0.0010 (4) | 0.0014 (5) | -0.0022 (4) |
| O2 | 0.0060 (6) | 0.0073 (5) | 0.0114 (6) | 0.0010 (4) | 0.0031 (5) | -0.0007 (4) |
| O3 | 0.0086 (6) | 0.0080 (5) | 0.0049 (5) | 0.0020 (4) | 0.0024 (5) | 0.0016 (4) |
| O4 | 0.0073 (6) | 0.0058 (5) | 0.0131 (6) | 0.0009 (4) | 0.0048 (5) | 0.0004 (5) |
| O5 | 0.0077 (6) | 0.0077 (5) | 0.0052 (5) | 0.0003 (4) | 0.0028 (5) | -0.0009 (4) |
| O6 | 0.0083 (6) | 0.0051 (5) | 0.0093 (6) | -0.0014 (4) | 0.0035 (5) | -0.0002 (4) |

Geometric parameters (\AA , $^\circ$)

| | | | |
|-----------------------|-------------|------------------------|-------------|
| Mg1—O3 ⁱ | 2.1224 (13) | Na1—O6 ^x | 2.4386 (13) |
| Mg1—O3 ⁱⁱ | 2.1224 (13) | Na1—O3 | 2.8840 (19) |
| Mg1—O1 ⁱⁱⁱ | 2.1312 (12) | Na1—O3 ^{ix} | 2.8840 (19) |
| Mg1—O1 ^{iv} | 2.1312 (12) | Na1—O1 ^{xi} | 2.922 (2) |
| Mg1—O4 ^v | 2.1669 (14) | Na1—O1 ^{viii} | 2.922 (2) |
| Mg1—O4 | 2.1669 (14) | P1—O1 ^v | 1.5372 (12) |
| Mg2—O6 | 2.0234 (13) | P1—O1 | 1.5372 (12) |
| Mg2—O3 ⁱⁱⁱ | 2.0686 (13) | P1—O2 ^v | 1.5476 (13) |
| Mg2—O2 | 2.0696 (14) | P1—O2 | 1.5476 (13) |

| | | | |
|---|-------------|---|-------------|
| Mg2—O5 ^{vi} | 2.0729 (13) | P2—O5 | 1.5234 (12) |
| Mg2—O5 ^{vii} | 2.0955 (13) | P2—O6 | 1.5263 (12) |
| Mg2—O1 ^{viii} | 2.1153 (14) | P2—O3 | 1.5349 (13) |
| Na1—O6 | 2.2974 (13) | P2—O4 | 1.5806 (13) |
| Na1—O6 ^{ix} | 2.2974 (13) | O4—H4 | 0.9269 |
| Na1—O6 ^{vii} | 2.4386 (13) | | |
| O3 ⁱ —Mg1—O3 ⁱⁱ | 104.23 (8) | O6 ^{vii} —Na1—O6 ^x | 166.01 (10) |
| O3 ⁱ —Mg1—O1 ⁱⁱⁱ | 86.53 (5) | O6—Na1—O3 | 56.06 (5) |
| O3 ⁱⁱ —Mg1—O1 ⁱⁱⁱ | 78.23 (5) | O6 ^{ix} —Na1—O3 | 111.84 (7) |
| O3 ⁱ —Mg1—O1 ^{iv} | 78.23 (5) | O6 ^{vii} —Na1—O3 | 62.51 (5) |
| O3 ⁱⁱ —Mg1—O1 ^{iv} | 86.53 (5) | O6 ^x —Na1—O3 | 105.27 (6) |
| O1 ⁱⁱⁱ —Mg1—O1 ^{iv} | 155.13 (8) | O6—Na1—O3 ^{ix} | 111.84 (7) |
| O3 ⁱ —Mg1—O4 ^v | 83.70 (5) | O6 ^{ix} —Na1—O3 ^{ix} | 56.06 (5) |
| O3 ⁱⁱ —Mg1—O4 ^v | 170.20 (5) | O6 ^{vii} —Na1—O3 ^{ix} | 105.27 (6) |
| O1 ⁱⁱⁱ —Mg1—O4 ^v | 108.38 (5) | O6 ^x —Na1—O3 ^{ix} | 62.51 (5) |
| O1 ^{iv} —Mg1—O4 ^v | 89.53 (5) | O3—Na1—O3 ^{ix} | 71.02 (6) |
| O3 ⁱ —Mg1—O4 | 170.20 (5) | O6—Na1—O1 ^{xi} | 118.48 (6) |
| O3 ⁱⁱ —Mg1—O4 | 83.70 (5) | O6 ^{ix} —Na1—O1 ^{xi} | 74.30 (5) |
| O1 ⁱⁱⁱ —Mg1—O4 | 89.53 (5) | O6 ^{vii} —Na1—O1 ^{xi} | 84.97 (5) |
| O1 ^{iv} —Mg1—O4 | 108.38 (5) | O6 ^x —Na1—O1 ^{xi} | 107.88 (6) |
| O4 ^v —Mg1—O4 | 89.05 (7) | O3—Na1—O1 ^{xi} | 146.62 (4) |
| O6—Mg2—O3 ⁱⁱⁱ | 85.88 (5) | O3 ^{ix} —Na1—O1 ^{xi} | 129.17 (3) |
| O6—Mg2—O2 | 88.80 (5) | O6—Na1—O1 ^{viii} | 74.30 (5) |
| O3 ⁱⁱⁱ —Mg2—O2 | 111.03 (6) | O6 ^{ix} —Na1—O1 ^{viii} | 118.48 (7) |
| O6—Mg2—O5 ^{vi} | 172.05 (6) | O6 ^{vii} —Na1—O1 ^{viii} | 107.88 (6) |
| O3 ⁱⁱⁱ —Mg2—O5 ^{vi} | 91.58 (5) | O6 ^x —Na1—O1 ^{viii} | 84.97 (5) |
| O2—Mg2—O5 ^{vi} | 85.07 (5) | O3—Na1—O1 ^{viii} | 129.17 (3) |
| O6—Mg2—O5 ^{vii} | 98.45 (5) | O3 ^{ix} —Na1—O1 ^{viii} | 146.62 (4) |
| O3 ⁱⁱⁱ —Mg2—O5 ^{vii} | 162.38 (6) | O1 ^{xi} —Na1—O1 ^{viii} | 51.46 (6) |
| O2—Mg2—O5 ^{vii} | 86.23 (5) | O1 ^v —P1—O1 | 111.21 (10) |
| O5 ^{vi} —Mg2—O5 ^{vii} | 86.22 (5) | O1 ^v —P1—O2 ^v | 111.07 (7) |
| O6—Mg2—O1 ^{viii} | 100.87 (6) | O1—P1—O2 ^v | 108.34 (7) |
| O3 ⁱⁱⁱ —Mg2—O1 ^{viii} | 79.79 (5) | O1 ^v —P1—O2 | 108.34 (7) |
| O2—Mg2—O1 ^{viii} | 166.18 (6) | O1—P1—O2 | 111.07 (7) |
| O5 ^{vi} —Mg2—O1 ^{viii} | 86.06 (5) | O2 ^v —P1—O2 | 106.73 (10) |
| O5 ^{vii} —Mg2—O1 ^{viii} | 82.62 (5) | O5—P2—O6 | 111.03 (7) |
| O6—Na1—O6 ^{ix} | 166.85 (10) | O5—P2—O3 | 111.42 (7) |
| O6—Na1—O6 ^{vii} | 86.56 (4) | O6—P2—O3 | 108.82 (7) |
| O6 ^{ix} —Na1—O6 ^{vii} | 91.84 (4) | O5—P2—O4 | 107.74 (7) |
| O6—Na1—O6 ^x | 91.84 (4) | O6—P2—O4 | 108.99 (7) |
| O6 ^{ix} —Na1—O6 ^x | 86.56 (4) | O3—P2—O4 | 108.78 (7) |

Symmetry codes: (i) $x-1/2, -y+1/2, z-1/2$; (ii) $-x+1/2, -y+1/2, -z+1$; (iii) $x, -y+1, z-1/2$; (iv) $-x, -y+1, -z+1$; (v) $-x, y, -z+1/2$; (vi) $-x+1/2, y+1/2, -z+1/2$; (vii) $x, -y+1, z+1/2$; (viii) $-x+1/2, -y+3/2, -z+1$; (ix) $-x+1, y, -z+3/2$; (x) $-x+1, -y+1, -z+1$; (xi) $x+1/2, -y+3/2, z+1/2$.

Hydrogen-bond geometry (Å, °)

| <i>D—H···A</i> | <i>D—H</i> | <i>H···A</i> | <i>D···A</i> | <i>D—H···A</i> |
|----------------|------------|--------------|--------------|----------------|
| O4—H4···O2 | 0.93 | 1.57 | 2.4932 (17) | 174 |